

Test Report

No. CANNR2123602401

Date: 22 Dec 2021

Page 1 of 3

FUZHOU TOPDA NEW MATERIAL CO., LTD

17-16, C3# BUILDING, CANGSHAN WANDA PLAZA, 216 PUSHANG AVENUE, FUZHOU, FUJIAN, CHINA

The following sample(s) was/were submitted and identified on behalf of the clients as : Dimethyl Silicone Oil

SGS Job No. : MNS211490GZ - GZ
Model No. : TPD-201 (350cSt)
Manufacturer : FUZHOU TOPDA NEW MATERIAL CO., LTD
Date of Sample Received : 14 Dec 2021
Testing Period : 14 Dec 2021 - 22 Dec 2021
Test Requested : Selected test(s) as requested by client.
Test Method : Please refer to next page(s).
Test Results : Please refer to next page(s).

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch

Allie Chen

Allie Chen
Approved Signatory



Test Results :

Test Part Description :

Specimen No.	SGS Sample ID	Description
SN1	CAN21-236024.001	Colorless transparent liquid

Remarks :

- (1) 1 mg/kg = 1 ppm = 0.0001%
- (2) MDL = Method Detection Limit
- (3) ND = Not Detected (< MDL)
- (4) "-" = Not Regulated

Siloxanes

Test Method : SGS In-house method (GZTC CHEM-TOP-206-01), analysis was performed by GC-MS.

<u>Test Item(s)</u>	<u>Unit</u>	<u>MDL</u>	<u>001</u>
Hexamethyl cyclotrisiloxane (D3)	mg/kg	30.0	127.7
Octamethyl cyclotetrasiloxane (D4)	mg/kg	30.0	156.6
Decamethyl cyclopentasiloxane (D5)	mg/kg	30.0	69.3
Dodecamethyl cyclohexasiloxane (D6)	mg/kg	30.0	43.7
Tetradecamethyl cycloheptasiloxane (D7)	mg/kg	30.0	ND
Hexadecamethyl cyclooctasiloxane (D8)	mg/kg	30.0	ND
Octadecamethyl cyclononasiloxane (D9)	mg/kg	30.0	ND
Eisosamethyl cyclodecasiloxane (D10)	mg/kg	30.0	ND
Sum(D3-D10)	mg/kg	-	397.3

Notes :

The results of D10 was based on semi-quantitative analysis and calculated by D9.



Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***

